
#### 4 COLOURS / 12 SIZES / 2 FINISHES / 0 SPECIAL PIECES

Influenced by the fine veining found within marquina marble, Muse translates into a choice of creating distinctive spaces with a sophisticated touch. Its natural and satin finishes replicates the natural wearing over time of the surface, offering a very pleasant feel. Available in 4 colours, comprising of a range of wall tiles endowed in a diverse selection of decorations which enrich and personalise spaces. In porcelain floor coverings, both satin and natural finishes are available, with the latter presenting increased slip resistance characteristics, suitable for areas where this may be a requirement.







# Muse





IVORY



WHITE PRISMA



GREY PRISMA









IVORY PRISMA




COAL PRISMA

Porcelain	10mm thick	
	Natural	Satin
443x888 rectified	√	$\checkmark$
145x888 rectified	√	$\checkmark$
592x592 rectified	√	$\checkmark$
600x600 non-rectified	$\checkmark$	$\checkmark$
72x295 rectified	√	$\checkmark$
295x295 square mosiac	√	$\checkmark$

Ceramic	8.5mm thick	11.7mm thick
	Satin	Satin
300x900 non-rectified		$\checkmark$
295x592 rectified	$\checkmark$	
300x600non-rectified	$\checkmark$	
340x340 basket mosiac	$\checkmark$	
295x295 square mosiac	$\checkmark$	
281x341 hexagonal mosiac	√	
180x210 diamond mosiac	√	

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.



### GROUP / Bla - PORCELAIN

#### MUSE SATIN

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	E <sub>b</sub> ≤ 0.5%	≤ 0.1%
Breaking strength	ISO 10545-4	≥ 1300N	Ave ≥ 1750N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm <sup>2</sup>	Ave min 40 N/mm <sup>2</sup>
Resistance to deep abrasion	ISO 10545-7	Declare Class	White & Ivory – PEI 4 Grey – PEI 3 Coal – PEI 2
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GUB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

### GROUP / Bla - PORCELAIN

#### MUSE NATURAL

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	E <sub>b</sub> ≤ 0.5%	≤ 0.1%
Breaking strength	ISO 10545-4	≥ 1300N	Ave ≥ 1360N
Modulus of rupture	ISO 10545-4	Ave Minimum 35 N/mm <sup>2</sup>	Ave min 35 N/mm <sup>2</sup>
Resistance to deep abrasion	ISO 10545-7	Declare Class	White & Ivory – PEI 4 Grey – PEI 3 Coal – PEI 2
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GUB	GB
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL

Slip resistance characteristics	Pendulum Dry (4S Slider 96)	Pendulum Wet (4S Slider 96)	,	Pendulum Wet (TRL Slider 55)	Recycled Content	15 %
	+36 PTV	+36 PTV	+36 PTV	Range Name	Muse	
Full range	+36	+36	+36			

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

## GROUP / BIII - CERAMIC

#### MUSE NATURAL

	Standard	Requirement	Established values
Length and width	ISO 10545-2	±0.6% ~ ±2mm	Conforms
Thickness	ISO 10545-2	±5% ~ ±0.5mm	Conforms
Straightness	ISO 10545-2	±0.5% ~ ±1.5mm	Conforms
Flatness	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Rectangularity	ISO 10545-2	±0.5% ~ ±2.0mm	Conforms
Water absorption	ISO 10545-3	E <sub>b</sub> ≤ 10%	Ave 17%
Breaking strength	ISO 10545-4	≥ 600N	≥ 600N
Modulus of rupture	ISO 10545-4	Ave min 12 N/mm <sup>2</sup>	Ave 13N/mm <sup>2</sup>
Thermal shock resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Resistant
Frost resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Resistant
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class GB	GA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	GLA
Resistance to stain	ISO 10545-14	Declare Value	Class 5
Reaction to fire	-	Class A1 A1/FL	A1 A1/FL

### Grout and trim available

Muse	Grout	Trim
		-
		-
		-
		-
		-
		-
		-

Recycled Content	15 %
Range Name	Muse

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.