

MAS

4 COLOURS / 2 SIZES / 1 FINISH / 0 SPECIAL PIECES

MAS is More. Commercial grade performance in a contemporary quarry style floor and wall tile, available in 4 colours and 2 sizes. MAS takes waste from the tile manufacturing process in Spain and fuses unique dry granulation technology with heritage experience to create stunning and sustainable tiles at 95%+ recycled content. The low carbon production process makes MAS the lowest CO2 tile on the market.



MAS



MAS



MAS



Grey



Charcoal




Red




Ochre

	9mm thick	Wall/floor	Interior/exterior
Ceramic	Matt	All tiles	All tiles
202x202	✓	Wall & Floor	Interior
99.5x202	✓	Wall & Floor	Interior



202x202x9



99.5x202x9

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles

MAS

GROUP / AIIa-2 – Extruded Ceramic

	Standard	Requirement	Established Values
Length and Width	ISO 10545-2	±1.25%	Conforms
Thickness	ISO 10545-2	±10%	Conforms
Straightness	ISO 10545-2	±0.5%	Conforms
Flatness	ISO 10545-2	±0.8%	Conforms
Rectangularity	ISO 10545-2	±1%	Conforms
Water Absorption	ISO 10545-3	Eb 3% ≤ 0.5%	0.6 %
Breaking Strength	ISO 10545-4	≥ 800N	1518N
Modulus of Rupture	ISO 10545-4	Ave Minimum 13 N/mm ²	>40 N/mm ²
Resistance to deep Abrasion	ISO 10545-6	≤541mm ³	162 mm ³
Thermal Shock Resistance	ISO 10545-9	Pass according to EN ISO 10545-1	Pass
Frost Resistance	ISO 10545-12	Pass according to EN ISO 10545-1	Pass
Resistance to household chemicals and swimming pool salts	ISO 10545-13	Min Class UB	UA
Resistance to high concentrations of alkalis and acids	ISO 10545-13	Declare Value	NPD
Resistance to low concentrations of alkalis and acids	ISO 10545-13	Declare Value	ULA
Resistance to Stain	ISO 10545-14	Min Class 3	Class 5
Reaction to Fire		Class A1 A1/FL	A1/FL

Slip Resistance Characteristics	Pendulum Dry (4S Slider 96) +36	Pendulum Wet (4S Slider 96) +36
Full Range	✓	✓

The colour representations shown in this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of our floor tiles there may be a small variation in the PTV value. The slip resistance values are correct at the time of testing and represent the standard production value. Inadequate cleaning and maintenance will lead to significant reduction in the slip resistance of any tiles. The pendulum test results have been displayed in line with H&S Executive guidelines whereby 0-24 represents high slip potential, 25-35 moderate slip potential & 36+ represents a low slip potential.

For further information contact: T: 0116 276 2532 – W: www.parkside.co.uk – E: info@parkside.co.uk

Strata Technical Tiles is the partner brand of Parkside Architectural Tiles